



DEMIRAGLAR®

MARBLE INDUSTRY & TRADE LTD

Natural & Beautiful

THE COMPANY

Demiraglar is a multinational company of Turkish origin which is a world leader in the sector of Natural Stone.

Since 1986, the year in which Demiraglar was established, it has experienced progressive growth and strong international expansion, and in so doing becoming a clear benchmark in the sector of Natural Stone and providing it with innovation and technology.

DEMIRAGLAR PHILOSOPHY AND VALUES:

Demiraglar's mission, with an elevated international vocation, goes further than the production and sale of the Natural Stone. It provides solutions to market demands and trends, sustaining itself by innovation, technology and customer service.

Demiraglar's vision is to become the world benchmark for the Natural Stone sector, by strengthening its leadership position, maximizing growth opportunities when in other avant-garde segments of the covering and floor market.

Values and Beliefs

- Constantly excelling
- Excellence in service
- Team spirit
- Respect and care for the environment

Major Demiraglar assets are:

- **A high response capacity:** With 6 of its own quarries, among which the greatest deposit in the world of Marble
- **Competitiveness and innovation:** we have 2 strategically located high tech factories.
- **Approach to our clients and a high orientation on the market:** we have more than 200 employees with broad experience in the sector
- **Wide selection:** we produce more than 1 million square meters a year with more than 40 different materials.
- **International presence:** we export to more than 40 countries and we have subsidiaries located throughout the world.



DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD

QUARRIES

The principle supply source of Demiraglar are its own quarries, which allow it to guarantee the supply of strategic materials and approach projects with great breadth.

The company has 6 of its own quarries for marble. From these quarries, Demiraglar, annually extracts more than 100 thousand tons of raw materials, thereby being the company with the greatest number of its own marble quarries throughout the world.

In addition, Demiraglar has preferential supply agreements for other quarries.









FACTORIES


Demiraglar has 2 factories and both of them strategically located at the middle of Marble Resources:

Demiraglar installations are the most modern in the sector, a result of its continuous investment efforts that permit it to attend to and solve with the maximum effectiveness the needs of their clients.

Slab and Cut-to-Size Production









MATERIALS

Demiraglar is committed to a wide range of unique and exclusive Natural Stone, facilitating the appropriate choice of materials in the world of current architecture and interior design. The diversity and chromatic wealth of Natural Stone, together with a large variety of solutions, finishes and formats allow original, different and avant-garde results that adapt nature to the latest trends in materials.

Its versatility, exclusivity and beauty make Demiraglar Natural Stone an irreplaceable value that helps to make any project, whether large or small, into a great work with excellent materials.

Demiraglar has its own 6 types of marble which are from its own quarries around Turkey.

DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD




SULTAN GOLD



ROYAL VIOLET



BIANCO LEOPARDO



BIANCO BELLA




FIRUZE (VERDE ROSA)



ROSA SILVER



VERDE ARABESCATO




DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD

Bianco Leopardo

Physical Properties	Unit	Value
Hardness	(Monhs)	3
Unit Weight	(gr/m ³)	2,76
Porosity	(%)	0,37
Woit Ratio	(%)	0,37
Water Absorption	(%)	0,13
Mechanial Properties		
Uniaxial Compressive strenght	(kg/cm ²)	1347
Bending Tensile Strenght	(kg/cm ²)	156
Abrasion Strenght by Friction	(cm ³ /50 cm ²)	22,12
lpact Strenght	(kg cm/cm ³)	10

TILE - SLAB - BLOCK





DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD

Sultan Gold

Physical Properties	Unit	Value
Hardness	(Mohs)	3
Unit Weight	(gr/m ³)	2,83
Porosity	(%)	0,66
Woit Ratio	(%)	0,66
Water Absorption	(%)	0,232
Mechanical Properties		
Uniaxial Compressive strenght	(kg/cm ²)	1257
Bending Tensile Strenght	(kg/cm ²)	50
Abrasion Strenght by Friction	(cm ³ /50 cm ²)	20,27
lpact Strenght	(kg cm/cm ³)	2

TILE - SLAB - BLOCK





DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD

Firuze (Verde Rosa)

Physical Properties	Unit	Value
Hardness	(Mohs)	3
Unit Weight	(gr/m ³)	2,7
Porosity	(%)	0,15
Woit Ratio	(%)	0,15
Water Absorption	(%)	0,058
Mechanical Properties		
Uniaxial Compressive strenght	(kg/cm ²)	778
Bending Tensile Strenght	(kg/cm ²)	102
Abrasion Strenght by Friction	(cm ³ /50 cm ²)	22,50
lpact Strenght	(kg cm/cm ³)	2

TILE - SLAB - BLOCK






DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD

Verde Arabescato

Physical Properties	Unit	Value
Hardness	(Mohs)	3
Unit Weight	(gr/m ³)	2,76
Porosity	(%)	0,37
Woit Ratio	(%)	0,37
Water Absorption	(%)	0,13
Mechanical Properties		
Uniaxial Compressive strenght	(kg/cm ²)	1347
Bending Tensile Strenght	(kg/cm ²)	156
Abrasion Strenght by Friction	(cm ³ /50 cm ²)	22,12
Ipact Strenght	(kg cm/cm ³)	10

TILE - SLAB - BLOCK





DEMIRAGLAR
MARBLE INDUSTRY & TRADE LTD

Royal Violet

Physical Properties	Unit	Value
Hardness	(Monhs)	3
Unit Weight	(gr/m ³)	2,7
Porosity	(%)	0,15
Woit Ratio	(%)	0,15
Water Absorption	(%)	0,058
Mechanical Properties		
Uniaxial Compressive strenght	(kg/cm ²)	778
Bending Tensile Strenght	(kg/cm ²)	102
Abrasion Strenght by Friction	(cm ³ /50 cm ²)	22,50
Ipact Strenght	(kg cm/cm ³)	2

TILE - SLAB - BLOCK





DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD

Rosa Silver

Physical Properties	Unit	Value
Hardness	(Mohs)	3
Unit Weight	(gr/m ³)	2,73
Porosity	(%)	0,17
Woit Ratio	(%)	0,17
Water Absorption	(%)	0,063
Mechanial Properties		
Uniaxial Compressive strenght	(kg/cm ²)	1130
Bending Tensile Strenght	(kg/cm ²)	172
Abrasion Strenght by Friction	(cm ³ /50 cm ²)	22,41
lpact Strenght	(kg cm/cm ³)	10,5

TILE - SLAB - BLOCK




DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD

Bianco Bella

Physical Properties	Unit	Value
Hardness	(Mohs)	3
Unit Weight	(gr/m ³)	2,7
Porosity	(%)	0,15
Woit Ratio	(%)	0,15
Water Absorption	(%)	0,058
Mechanical Properties		
Uniaxial Compressive strenght	(kg/cm ²)	778
Bending Tensile Strenght	(kg/cm ²)	102
Abrasion Strenght by Friction	(cm ³ /50 cm ²)	22,50
Ipact Strenght	(kg cm/cm ³)	2

TILE - SLAB - BLOCK

DEMIRAGLAR[®]
MARBLE INDUSTRY & TRADE LTD




CALACATTA PAONAZZO




CALYPSO PEARL



SULTAN GOLD



CALACATTA ORO



BLUE LAKE



CALACATTA PAONAZZO



CALACATTA ORO



PROJECTS

Only a leading organization such as Demiraglar with the capacity of mobilizing large resources can carry out large architectural projects.

Product of its experience in large works, Demiraglar has a Projects Department the mission of which is to promote the company's materials in large projects around the world. This highly-specialized team, also carries out research on constructive systems applicable to the entire array of Demiraglar products.

Demiraglar works with architects and engineers in the application of their materials in pavements, coverings, ventilated facades and any other technical solution, thereby collaborating in order to make any Project a reality.

For more information: info@demiraglar.com



Hyundai Insurance Building / Korea - Bianco Leopardo Project




Suhan 360 Hotel





Verde Rosa (Firuze) Project



Chetau Star River Hotel / Sultan Gold



Verde Rosa (Firuze) Project





DEMİRAGLAR®
MERMER SANAYİ ve TİCARET LTD. ŞTİ.

DEMEKS
PAZARLAMA İTH.- İHR. LTD. ŞTİ.

Headquarter

Nazilli O.S.B. 3. cadde, No: 9 Nazilli - AYDIN TURKEY
Phone : +90 (256) 316 31 65 • Fax: +90 (256) 316 31 66
e- mail: info@demiraglar.com
Web : www.demiraglar.com

Factory : Slab and Cut-to-Size production

Nazilli O.S.B. 3. cadde, No: 9 Nazilli - AYDIN TURKEY

Quarry: Yazır Köyü - Karacasu - AYDIN - TURKEY